

AllOffice



Parameter	Standard	Enhet	Värde
Gramvikt	ISO 536	g/m ²	80
Tjocklek	ISO 534	µm	106
Bulk	ISO 534		1,33
Fukthalt	ISO 287	%	4,1
Ytråhet	ISO 8791	Bendtsen ml/min	220
Vithet	ISO 11475	CIE	150
Ljushet	ISO 2470-2	%	107
Opacitet	ISO 2470-2	%	92

