



## Maintenance Oil

#### Revitalises oil-treated wood

Maintenance Oil may be used for the maintenance of all oxidative oiled wood surfaces and is especially suitable for the regular maintenance of oiled wood floors. In addition to being very easy to use and assuring minimal product waste, the maintenance oil refreshes the natural, warm glow of the wood and increases resistance to stains and waste. Maintenance Oil is suitable for both manual and machine application to oiled floors.

- Makes oiled floors even more durable
- Highlights the glow and the grain structure of the wood
- Gives the wood a beautiful, breathable surface
- Indoor climate certified
- Easy to apply

## Application area

For care and maintenance of all oxidative oiled wood surfaces, especially floors. Can be applied manually with a polishing pad and by machine (floors larger than 8-10 m²).

## Work description

#### **Preparation**

Product, room and floor temperature should be between 15–35°C. Ensure good ventilation at all times during the application and drying time. Clean the floor with WOCA Intensive Wood Cleaner. Leave the floor to dry for at least 8 hours. The floor must be completely dry.

#### Always Remember

Always remember to test on a less visible spot to check the compatibility of the surface with the product.

#### Treatment

Shake the container carefully. Apply approx. 1 dl oil per 4 m2 with pad, short-haired paint roller, cotton cloth or use polishing machine for large surfaces. It is important that the Maintenance Oil is carefully polished into the wood. Continue polishing until the wood appears saturated and the surface looks uniform. Wipe the floor with clean, dry cotton cloths before proceeding with the next section of floor to be finished. The floor should not appear wet and there should not be any excess oil left on the surface after polishing. Continue stepwise till the floor has been finished.

#### Please note

Do not clean the floor or expose it to water during the first 3 days, while the oil is curing.

#### Drying time

Drying time when machine polished: 3-4 hours at 20°C

Drying time when hand polished: 24-48 hours at 20°C

Fully hard: 3 days at 20°C

## WOCA ·

## Technical data

VOC: 480 g/l, maximum VOC content (A/f (SB)): 700 g/l.

Density: 0.85-0.90 g/ml.

Shelf life: 3 years

Application Temperature: +15-30°C and approx. 50% air humidity.

Coverage: 30-40 m<sup>2</sup>/L
Colours: Natural, White

Cleaning of tools: Use WOCA Solvent or turpentine

Storage: +10-25°C. Keep out of reach of children. Do not expose to heat (e.g.

sunlight). Store frost-free during winter and cool during summer.

Packaging: 750 ML, 1 L, 2.5 L Viscosity: 15-20 Sec. DIN Cup 4

Dilution: Undiluted

Odour: Characteristic

Solid content: 40-50%

# Maintenance and related products

#### Maintaining and cleaning

For daily cleaning, WOCA Natural Soap is recommended, which effectively washes and cares for the wood. Supplement occasionally with WOCA Oil Refreshing Soap, which also adds a little oil to the wood with each wash.

WOCA Denmark A/S Tværvej 6 DK - 6640 Lunderskov +45 9958 5600 info@wocadenmark.com wocadenmark.com This information is based on extensive laboratory testing and practical experience. Because the conditions under which the product is used are often beyond the control of WOCA Denmark, we can only guarantee the quality of the actual product. WOCA Denmark A/S accepts no liability for incorrect use and handling of the product. In principle, this product can be considered an intermediate product, as results depend on construction, the nature of the surface, pretreatment, temperature, air humidity, application etc. WOCA Denmark A/S reserves the right to change the product and the stated information without notice. This label/product description replaces all previous versions.